




Ceramabond™ 685-N bonds infrared heater.




Ceramabond™ 835-M bonds halogen lamp.



Ceramabond™ 503 coats heater used to 1700 °C.



Ceramabond™ 685-N bonds ceramic honeycomb to cylinder housing.



Ultra-Temp™ 516 seals heater assembly.

Aremco's high temperature ceramic adhesives are formulated using a broad range of ceramics fillers and inorganic binders, and are ideal for bonding, potting and sealing ceramics, composites, graphite, refractory metals, quartz, and semiconductors for applications to 3200 °F (1760 °C).

TYPICAL APPLICATIONS

Electrical

- Halogen Lamps
- Heaters
- Igniters
- Fiberoptics
- Resistors
- Solid Oxide Fuel Cells

Instruments & Sensors

- Gas Chromatographs
- High Vacuum Components
- Liquid Metal Inclusion Counters
- Mass Spectrometers
- Oxygen Analyzers
- Strain Gauges
- Semiconductors
- Temperature Probes

Mechanical

- Ceramic Honeycombs
- Ceramic Textiles
- Graphite Blocks
- Refractory Insulation
- Sagger Plates
- Thread-Locking

Part No.	Filler	Bonding*	Principal Use	
503	Al ₂ O ₃	C-C	Dense Ceramics; Alumina-to-Alumina	
552		C-C, C-M	Solid Oxide Fuel Cells; Low CTE Metals	
569		C-C, C-M, Quartz	Probes, Sensors, Resistors, Igniters, Heaters	
670		C-C, C-M	Ceramic Textiles, Thread-Locking	
671		C-C, C-M, M-M	Ceramic Textiles, Thread-Locking	
835-M		C-C, C-M, Quartz	Halogen Lamps	
835-MB		C-C, C-M, Quartz	Halogen Lamps	
865		AlN	C-C, C-M	Probes & Sensors; Thermal Conductivity
600-N		Al ₂ O ₃ - SiO ₂	C-C, C-M	Refractory Repair
668			C-C, C-M	Oxygen Sensors, Heaters
571	MgO	C-M, M-M	Heaters, Induction Coils, Sensors	
632	Mica	Mica	Mica Heaters	
618-N	SiO ₂	C-C, Quartz	Porous Ceramics, Quartz Tubes & Vessels	
516	ZrO ₂	C-C, C-M	Thermocouples, Semiconductor Wafers	
685-N		C-C, C-M	Gasketing, Heaters, Igniters	
835		C-C, C-M	Halogen Lamps	
885		C-C	Zirconia, Solid Oxide Fuel Cells	
890		SiC	C-C	Crucibles, Heaters, Sagger Plates

*C-C = Ceramic-to-Ceramic C-M = Ceramic-to-Metal M-M = Metal-to-Metal

HIGH TEMPERATURE CERAMIC ADHESIVES PROPERTIES

Part Number	503	552	569	670	671	835-M	835-MB	600-N	668	
Tradename	Ceramabond™									
Major Constituent	Al ₂ O ₃						Al ₂ O ₃ – SiO ₂			
Color	White	White	White	White	White	White	White	Tan	White	
Temperature Limit, °F (°C)	3000 (1650)	3000 (1650)	3000 (1650)	3000 (1650)	3200 (1760)	3000 (1650)	3000 (1650)	3000 (1650)	2500 (1371)	
No. Components	1	1	1	1	1	1	2	1	1	
Viscosity, cP	50,000–90,000	53,000–73,000	Paste	2,500–5,000	40,000–80,000	30,000–40,000	40,000–80,000	5,000–15,000	40,000–80,000	
Specific Gravity, g/cc	2.35–2.55	1.90–2.20	2.15–2.30	1.80–1.95	2.05–2.15	2.35–2.45	2.00–2.15	2.00–2.05	2.20–2.40	
CTE, in/in/°F × 10 ⁻⁶ (°C)	4.0 (7.2)	4.3 (7.7)	4.2 (7.6)	4.3 (7.7)	4.3 (7.7)	4.0 (7.2)	3.8 (6.8)	3.0 (5.4)	4.0 (7.2)	
Handling	Mix Ratio, powder:liquid	NA	NA	NA	NA	NA	NA	100 : 60–80	NA	NA
	Thinner	503-T	552-T	569-T	670-T	671-T	835-M-T	835-MB-T	600-T	668-T
	Solvent	Water	Water	Water	Water	Water	Water	Water	Water	Water
	Application Temperature, °F	50–90	50–90	50–90	50–90	50–90	50–90	50–90	50–90	50–90
	Storage Temperature, °F	40–90	40–90	40–90	40–90	40–90	40–90	40–90	40–90	40–90
Curing	Shelf Life, months	6	6	6	6	6	6	6	6	
	Air Set, hrs	≤ 1	1–4	1–4	1–4	1–4	1–4	1–4	1	
	Heat Cure, °F, hrs	200, 2 + 500, 2 + 700, 2	200, 2 + 500, 2	200, 2	200, 2	200, 2	200, 2 + 350, 2 + 500, 2	200, 2 + 350, 1	200, 1–4	
	Dielectric Strength, volts/mil @ RT	171	173	138	142	182	163	202	203	118
	Torque Strength, ft-lbs ¹	60	52	38	60	57	63	27	14	38
	Moisture Resistance ²	Good	Excellent	Excellent	Excellent	Excellent	Good	Good	Excellent	Excellent
	Alkali Resistance ²	Fair	Good	Good	Good	Excellent	Excellent	Good	Excellent	
	Acid Resistance ²	Excellent	Good	Excellent	Good	Good	Good	Good	Good	

Footnotes

¹ Tested using a torque wrench after bonding a pre-oxidized ½”–13 nut and bolt and final curing at 1000 °F.

² Properties were evaluated after curing at 700 °F for 2 hours.

General Notes

1. Ceramabond adhesives do not contain volatile organic compounds (VOCs).
2. Special pigments available upon request.
3. Many adhesives including 503, 516, 552, 569, 571, 618-N, 671, 835-M, and 890 can be formulated using 1-5 micron ceramic powders. Add “-VFG” to the part number (eg. 503-VFG).

Abbreviations

NA Not Applicable
NM Not Measured

HIGH TEMPERATURE CERAMIC ADHESIVES PROPERTIES

Part Number	865	571 ³	632	618-N	890 ⁴	516	685-N	835	885 ⁴
Tradename	Ceramabond™								
Major Constituent	AlN	MgO	Mica	SiO ₂	SiC	ZrO ₂ – ZrSiO ₄			
Color	Gray	Off-White	Tan	Off-White	Blue-Gray	Tan	Tan	Tan	Tan
Temperature Limit, °F (°C)	3000 (1650)	3200 (1760)	2300 (1260)	3000 (1650)	3000 (1650)	3200 (1760)	3000 (1371)	3000 (1371)	3200 (1760)
No. Components	1	2	1	1	1	1	1	1	1
Viscosity, cP	Paste	20,000–90,000	10,000–25,000	40,000–60,000	35,000–55,000	40,000–70,000	5,000–20,000	20,000–40,000	10,000–20,000
Specific Gravity, g/cc	1.95–2.15	1.90–2.20	1.45–1.50	1.80–1.90	1.70–1.75	2.15–2.30	1.85–1.95	2.25–2.35	2.65–2.70
CTE, in/in/°F × 10⁻⁶ (°C)	1.5 (2.7)	7.0 (12.6)	4.7 (8.5)	.33 (.59)	2.4 (4.4)	4.1 (7.4)	4.5 (8.1)	4.0 (7.2)	4.0 (7.2)
Handling	Mix Ratio, powder:liquid	NA	1.0:1.0, 1.5:1.0	NA	NA	NA	NA	NA	NA
	Thinner	865-T	571-T	632-T	618-N-T	890-T	516-T	685-N-T	835-T
	Solvent	Water	Water	Water	Water	Water	Water	Water	Water
	Application Temperature, °F	50–90	50–90	50–90	50–90	50–90	50–90	50–90	50–90
	Storage Temperature, °F	40–90	40–90	40–90	40–90	40–90	40–90	40–90	40–90
Curing	Shelf Life, months	6	6	6	6	6	6	6	6
	Air Set, hrs	1–4	1–4	1–4	1–4	≤1	1–4	1–4	≤1
	Heat Cure, °F, hrs	200, 2 + 350, 2 + 500, 2	200, 2	200, 2 + 500, 2	200, 2 + 500, 2 + 700, 2	200, 2 + 500, 2 + 700, 2	200, 2 + 500, 2 + 700, 2	200, 2	200, 2
Dielectric Strength, volts/mil @ RT	187	91	150	156	73	188	176	111	105
Torque Strength, ft-lbs¹	27	22	2	77	40	50	35	50	40
Moisture Resistance²	Excellent	Excellent	Good	Excellent	Good	Good	Excellent	Good	Good
Alkali Resistance²	Good	Good	Good	Good	Good	Excellent	Good	Good	Good
Acid Resistance²	Good	Fair	Good	Good	Good	Good	Good	Good	Good

Footnotes

- ¹ Tested using a torque wrench after bonding a pre-oxidized ½”–13 nut and bolt and final curing at 1000 °F.
- ² Properties were evaluated after curing at 700 °F for 2 hours.
- ³ Ceramabond™ 571 ranges for viscosity and specific gravity reflect a powder-to-liquid mix ratio that ranges from 1-to-1 to 1.5-to-1.
- ⁴ Ceramabond™ 885 and 890 are also available in high pH, silicate-bonded systems. Part numbers are 885-K and 890-K. Contact Aremco for special pricing.

General Notes

1. Ceramabond adhesives do not contain volatile organic compounds (VOCs).
2. Special pigments available upon request.
3. Many adhesives including 503, 516, 552, 569, 571, 618-N, 671, 835-M, and 890 can be formulated using 1-5 micron ceramic powders. Add “-VFG” to the part number (eg. 503-VFG).

Abbreviations


- | | |
|----|----------------|
| NA | Not Applicable |
| NM | Not Measured |

DESIGN GUIDELINES

General design criteria for bonding with ceramic adhesives are similar to those for epoxy adhesives. Main considerations include the **coefficient of thermal expansion, joint design, glue line thickness, and operating environment.**

Coefficient of Thermal Expansion

CERAMIC-TO-METAL RECOMMENDED DESIGN




Due to the high thermal loading implicit in most ceramic adhesive applications, the joint design should account for the difference in the coefficient of thermal expansion between the adhesive and the components that are being joined. In the illustration above, note that the “poor” design loads the adhesive in tension since the metal expands faster than the ceramic. The “good” design allows for this thermal mismatch and loads the adhesion in compression, offering higher reliability.

Joint Design

Most adhesives offer relatively poor tensile-shear strength, so it is important to design a joint that will distribute the mechanical stress by maximizing the length of the glue line as shown in this illustration.

CERAMIC-TO-CERAMIC RECOMMENDED JOINT DESIGN



Glue Line Thickness

The clearance between mating parts at operating temperature should be 2–8 mils (50–200 microns). Less than 2 mils will prevent uniform adhesion; greater than 8 mils will often result in cohesive shear failure within the adhesive. A maximum depth of 0.25” is recommended when using a ceramic adhesive for a small potting application.

Operating Environment

These adhesives offer excellent chemical, electrical and ultra high thermal resistance, and do not outgas under high vacuum. The main limitations are (a) relatively low mechanical strength and (b) slight porosity after curing. Contact Aremco for suggestions about how to reduce porosity and produce gas-tight seals.

APPLICATION PROCEDURES

Surface Preparation

Smooth surfaces are difficult to bond and should be etched, abrasive blasted or oxidized, then cleaned thoroughly prior to application. Aremco’s Corr-Prep™ CPR2000 is recommended for etching metals. Porous substrates should be pre-coated with a binder (thinner) to prevent separation and absorption of the adhesive binder. Add a “-T” to the part number (eg. 503-T) to designate the product thinner.

Mixing

One-part adhesives tend to settle and should be mixed thoroughly prior to use. Refer to Tech Bulletin A12 for information about Aremco’s **Model 7000 Pneumatic Mixer**. Mix ratios for two-part adhesives are shown in the Property Chart. Viscosity may be adjusted by thinning up to 20% by weight.

Application


Apply a thin coat of adhesive to each surface using a brush, spatula or dispenser. Using a clamp or similar tool, maintain a uniform glue line of 2–8 mils (200–500 microns) by applying even pressure across the assembly. Wipe away excess material prior to drying. Refer to Tech Bulletin A12 for optional dispensing tools.



Model 7000 Mixer

Curing


Refer to the Property Chart for specific curing instructions for each product.




Ceramabond™ 835-M bonds heat sink to halogen lamp.



Ceramabond™ 569 bonds flex heater to quartz vessel.




Ceramabond™ 503 coats spiral cantilevered sensor.




Ceramabond™ 569 bonds IR heater to ceramic insulator.



Cerabond™ 571 coats copper induction heater.



Cerabond™ 571 coats oxygen sensor.



Cerabond™ 571 bonds thermocouple to glass.




Cerabond™ 618-N bonds porous ceramic filter elements.



Cerabond™ 671 used as a high temp threadlocker.



Cerabond™ 503 repairs furnace saggar plate.



Cerabond™ 685-N bonds ceramic gasket.



Ultra-Temp™ 516 bonds thermocouple to quartz tube.




Cerabond™ 835 bonds halogen lamp.



Cerabond™ 552 seals thermocouple in metal housing.



Cerabond™ 835-M bonds cover to halogen lamp.



Cerabond™ 835-M bonds halogen lamp.

CERAMIC ADHESIVE SELECTOR CHART

Material	CTE °F (°C)	503	552	569	670	671	835-M	835-MB	600-N	600-HV	668	865	571	632	618-N	890	516	685-N	835	885	
					Al ₂ O ₃					Al ₂ O ₃ – SiO ₂			AlN	MgO	Mica	SiO ₂	SiC	ZrO ₂ – ZrSiO ₄			
Alumina	4.4 (7.9)	•	•	•	•	•	•	•			x		x								
Alumina-Silica	1.8 (3.2)								x	x	•										
Aluminum Nitride	1.5 (2.7)											•			x						
Beryllia	4.1 (7.4)	•	x	x	x	x	x										x	x	x	x	
Boron Carbide	2.6 (4.7)	x									x					x					
Boron Nitride	4.2 (7.6)	x																			
Borosilicate Glass	1.8 (3.2)	x													•						
Calcium Silicate	3.0 (5.4)				•																
Ceramic Textile	–				•	x												x			
Cordierite	1.1 (2.0)														•						
Graphite	4.3 (7.7)	x														x					
Macor	5.2 (9.4)		x	•	x	x	x				x		x	x							
Mica	4.7 (8.5)													•							
Mullite	3.0 (5.4)	x	x	x	x						•						x	x	x		
Quartz	0.30 (0.54)	x		x			x	x			x				•				x		
Refractory, Dense	–	•														•					
Refractory, Light Weight	–								•	•											
Sapphire	4.2 (7.6)	•		x	x		x	x			x										
Silica	0.31 (0.56)										x				•						
Silicon Carbide	2.9 (5.2)	x														•					
Silicon Nitride	1.8 (3.2)	x									x	x			x	x					
Steatite	4.0 (7.2)		x	•		x	x	x			x							x	•		
Zirconia	5.7 (10.3)																x	x	x	•	
Zirconia Silicate	4.0 (7.2)																•	•	•	x	
Aluminum	15.0 (27.0)												•								
Brass	10.2 (18.4)												•								
Cast Iron	5.9 (10.6)		x	x	x	x	x				x		•	x				x			
Copper	9.3 (16.7)												•								
Inconel	6.4 (11.5)		x	x	x	x	x				x		•								
Molybdenum	2.9 (5.2)		x	•	x	x	x				•						x	x	x		
Nickel	7.2 (13.0)												•								
Nickel-Iron	2.6 (4.7)		x	•	x	x	x				•						x	x	x		
Platinum	4.9 (8.8)	•	x	x	x																
Silicon	1.6 (2.9)										x	x					x	x	x		
Silver	10.6 (19.1)												x								
Stainless (300 Series)	9.6 (17.3)										x		x								
Stainless (400 Series)	6.2 (11.2)		x	x	x	x	x				x		•				x	x	x		
Steel (1010)	6.5 (11.7)		x	x	x	x	x				x		•				x	x	x		
Tantalum	3.9 (7.0)		x	x	x	x	x				•		x				x	x	x		
Titanium	5.8 (10.4)		x	x	x	x	x				x		•				x	x	x		
Tungsten	2.5 (4.5)		x	•	x	x	x				•						x	x	x		

• = Preferred, x = Applicable

Refer to Price List for availability of sample kits and complete order information.

Aremco Products makes no warranty express or implied concerning the use of this product.

The user assumes all risk of use or handling whether or not in accordance with directions or suggestions, or used singly or in combination with other products.